

# MUSEUM

## CALACATTA EXTRA GOLD NT/150X320

|           |   |             |
|-----------|---|-------------|
| Modèle    | <b>CALACATTA EXTRA GOLD NT/150X320</b>  |             |
| Référence | <b>32059</b>                            | <b>GOLD</b> |
| Taille    | <b>150X320</b>                          | cm          |
| Epaisseur | <b>12,00</b>                            | mm          |
| Finition  | <b>Natural</b>                          |             |
| Type      | <b>PORCELANICO - GRUPO BIa</b>          |             |
|           | <b>GL - Carreaux céramiques EMAILLE</b> |             |

### Caractéristiques mécaniques

|                 |                              |               |
|-----------------|------------------------------|---------------|
| EN ISO 10545-11 | Résistance au tressailage    | <b>Cumple</b> |
| EN ISO 10545-12 | Résistance au gel            | <b>Cumple</b> |
| EN ISO 10545-9  | Résistance au choc thermique | <b>Cumple</b> |

### Caractéristiques Superficielles

|                |                                  |                                |
|----------------|----------------------------------|--------------------------------|
| EN ISO 10545-7 | Effets visibles à x tour/min     | -                              |
| EN ISO-10545-6 | Résistance à l'abrasion profonde | <b>&lt; 175 mm<sup>3</sup></b> |
| EN-101         | Dureté/Résistance aux rayures    | <b>6</b>                       |

### Caractéristiques chimiques

|                 |   |                    |
|-----------------|---|--------------------|
| EN ISO-10545-13 | Acides et bases de hautes concentration | <b>---/---/---</b> |
| EN ISO-10545-13 | Acides et bases de faible concentration | <b>---/LA/LA</b>   |
| EN ISO-10545-13 | Produits de nettoyage domestique        | <b>A/A</b>         |
| EN ISO-10545-14 | Résistances aux taches                  | <b>5/-/5/5</b>     |

### Marquage CE



Déclaration de Performances

**001CPR2017-08-01**

Before laying the tiles, check the shade, calibre and quality. No claims will be accepted once the tiles have been laid. Leave a tile joint of at least 0.5 mm in the case of rectified tiles and 1.5 mm for non-rectified ones. The tile colour shown in this data sheet is merely indicative and it might differ from the real tile colour. This document is purely for sales purposes and it cannot be used in any legal or administrative proceedings, in a witness statement, or as documentary proof without the express permission of PERONDA GROUP.